


Lansurf SML20

Specification	Appearance at 25°C	:	Clear amber liquid free from foreign matter
	Saponification Value mg.KOH/g	:	40.0 - 50.0
	Acid Value mg.KOH/g	:	2.0 Max
	Water Content %	:	3.0 Max
	Hydroxyl Value mg.KOH/g	:	96.0 - 108.0

Typical Properties	Composition	:	Sorbitan Mono Laurate Ethoxylate
	CAS Number	:	9005-64-5
	Moles of EO	:	20
	Solids Content %	:	100
	Odour	:	Characteristic
	HLB Value	:	16.5
	Viscosity at 25°C (cP)	:	984
	Specific Gravity at 20°C	:	1.1
	Solubility in Water	:	Soluble
	Pour Point °C	:	<0
	Flash Point Closed Cup °C	:	>150

Foam Height Scale



Wetting Scale



Typical properties are based on our own measurements and do not constitute part of the sales specification

Application Lansurf SML20 can be used singularly or in combination with esters such as Lansurf SML. Typical applications include agrochemical formulations, as anti-fogging agents in plastic films, textile fibre lubricants and softener and as secondary emulsifiers in suspension and emulsion polymerisation. This product is also found to be readily biodegradable and would not expect to persist indefinitely in the environment.

Packaging Lansurf SML20 can be supplied in bulk road tankers, IBC's, 200kg nett drums.

Storage Stainless steel, polyethylene or glass lined equipment is necessary for the storage of Lansurf SML20 in order to prevent corrosion and subsequent contamination. This material can separate on standing and at low temperatures. May require agitation and warming prior to use.

All information, recommendations and suggestions appearing in the literature concerning the use of the product are based upon tests and data believed to be reliable. However it is the users responsibility to determine the suitability for their own use of the products described here. For non English datasheets translation has been carried out using translation software, Lankem accepts no liability due to errors that occur during translation.

Lankem Ltd
 Charles Street
 Dukinfield
 Cheshire
 SK16 4SD
 United Kingdom

Tel : 44 (0)161 343 3355
 Fax : 44 (0)161 343 3366

technical@lankem.co.uk
 www.lankem.eu

